MIGINOX FC 316L

FCAW STAINLESS STEEL

CLASSIFICATION:

EN ISO 17633-B TS 316L PC1 1

TS 316L PM21 1

APPROVALS: CE

KEY FEATURES:

- Rutile based extra low carbon gas shielded stainless steel FCW
 wire
- Typical 18Cr/12Ni/2.5Mo weld deposit
- Controlled ferrite content ensures resistance against cracking
- Improved corrosion, pitting and intergranular corrosion resistance
- Stable arc and low spatter
- Excellent bead appearance
- Easy slag removal
- Radiographic weld quality

TYPICAL APPLICATIONS:

- Welding of AISI 316, 316L, 317, 317L, 318 type stainless steel and similar grade
- Welding pipes, tubes and vessels
- Cladding stainless steels

 Application in textile processing, Naval and Chemical environments, Paper and pulp, Paint and dye industries, Food processing industries

CHEMICAL COMPOSITION OF UNDILUTED WELD METAL, Wt %:

| С | Mn | Si | Cr | Ni | Мо |
|----------|-----------|---------|-----------|-----------|---------|
| 0.04 max | 0.50-2.50 | 1.0 max | 17.0-20.0 | 11.0-14.0 | 2.0-3.0 |

| MECHANICAL PROPERTIES OF ALL WELD METAL: | | | | |
|------------------------------------------|-----------|----------|--------|--|
| | Condition | UTS, MPa | EL% | |
| Specification | As Welded | 485 min | 30 min | |

| PARAMETERS - PACKING DATA: | | | | | | |
|----------------------------|---------------------------------|-------------------------------------------------------------------------------------|--------------------------------------|--|--|--|
| Ø, mm 1.2 1.6 | Kg/Spool 12.5 12.5 | STORAGE / HANDLING : Keep dry and follow handling instructions mentioned on the box | All Positions, Except Vertical Down: | | | |

| Shielding Gas | Gas Flow Rate, LPM |
|------------------------|--------------------|
| CO ₂ | 15-20 |
| 80Ar+20CO ₂ | 18-25 |

It can work with CO2 sheilding gas.

